

ACROPARS 100

Heat Cure Acrylic Resin For Denture Base

This product is designed based on methyl methacrylate copolymers comply with ISO 1567 and ADA No. 12. ACROPARS 100 has excellent performance for preparing complete and partial dental prosthesis.

APPLICATION:

- 1- Making full denture prosthesis.
- 2- Making partial denture.

ADVANTAGE:

- 1- Adequate time for mixing and molding.
- 2- Curing time, 30 min. in boiling water.
- 3- Low water absorption.
- 4- High mechanical properties.
- 5- Good adhesion to synthetic teeth.
- 6- Good polishing property.
- 7- Excellent color stability.
- 8- No bubble and whitening in prosthesis.

SPECIFICATION:

No	Specification	Unit	Obtained	Required
1	Dough time	Sec	30	25-35
2	Molding time	min	25	>14
3	Curing time	min	30	30-40
4	Wate adsorption	$\mu\text{g}/\text{mm}^3$	4	<32
5	Transverse deflection	mm	3	2-5.5

PACKAGING:

Powder 500 gr in PE bottles
 10 kg in laminate bag
 Liquid 250 ml in glass bottles

ET73300

Marlic Medical Industries Co.

No. 33, Malekian Alley, Iranshahr
 St.; Karimkhan Zand Ave.
 Tehran- Iran

Tel: (+98-21) 88318502
 Fax: (+98-21) 88820843
 E- Mail: info@marlic.com

Zip Code: 1584786613
 Web Site: www.marlic.com

